















# ORGANIC PIGMENTS

FOR PAINT AND COATINGS, PLASTIC MATERIALS,  
LEATHER AND OTHER SPECIAL APPLICATIONS



NOVA

FULL SHADE	TINT SHADE	LIGH FASTNESS		WEATHER FASTNESS	CHEMICAL FASTNESS				
		FULL SHADE	1/25 ST SHADE		FULL SHADE	HEAT C°	OVER SPRAY	DENSITY g/cm³	HCL 2,5%
		7-8	6-7	4-5	140	4	1,4	5	5
<b>NOVA YELLOW 2 GX-70S</b> C.I. Pigment Yellow 74 • C.I. N° 11714									
		7-8	5-6	4	160	3	1,4	5	5
<b>NOVA YELLOW 5 GX-TS</b> C.I. Pigment Yellow 74 • C.I. N° 11714									
		7-8	7	3-4	200	5	1,4	5	5
<b>NOVA YELLOW ST H10G</b> C.I. Pigment Yellow 81 • C.I. N° 21127									
		6-7	4-5	3	160	5	1,4	5	5
<b>NOVA YELLOW HRB</b> C.I. Pigment Yellow 83 • C.I. N° 21108									
		6-7	5	4	150	5	1,2	5	5
<b>NOVA YELLOW HRB 70</b> C.I. Pigment Yellow 83 • C.I. N° 21108									
		7	7	4-5	240	5	1,4	5	5
<b>NOVA YELLOW 3G</b> C.I. Pigment Yellow 93 • C.I. N° 20710									
		7	7	5	240	4-5	1,4	5	5
<b>NOVA YELLOW GR</b> C.I. Pigment Yellow 95 • C.I. N° 20034									

The technical data above stated are presented in good faith and to the best of our knowledge. They should serve only as approximate guidance and therefore customers are kindly advised to test and ascertain the performance of our products in the operating conditions existing at their end, to satisfy themselves about their suitability in a given industrial application.















**NOVACHEM**

## ORGANIC PIGMENTS

FOR PAINT AND COATINGS, PLASTIC MATERIALS,  
LEATHER AND OTHER SPECIAL APPLICATIONS



NOVA

FULL SHADE	TINT SHADE	LIGH FASTNESS		WEATHER FASTNESS	CHEMICAL FASTNESS				
		FULL SHADE	1/25 ST SHADE		FULL SHADE	HEAT C°	OVER SPRAY	DENSITY g/cm <sup>3</sup>	HCL 2,5%
		7-8	7-8	4	200	5	2,1	5	5
<b>NOVA FAST YELLOW 2RLTB</b> C.I. Pigment Yellow 110 • C.I. N° 56280									
		7-8	7-8	4	200	5	1,9	5	5
<b>NOVA FAST YELLOW 3RLTB</b> C.I. Pigment Yellow 110 • C.I. N° 56280									
		7-8	7-8	4-5	200	5	1,5	5	5
<b>NOVA FAST YELLOW 8GN</b> C.I. Pigment Yellow 128 • C.I. N° 20037									
		7-8	7	4-5	200	5	1,8	5	5
<b>NOVA YELLOW ST-960</b> C.I. Pigment Yellow 138 • C.I. N° 56300									
		8	7-8	4-5	200	5	1,7	5	5
<b>NOVA YELLOW ST 4021 VG</b> C.I. Pigment Yellow 139 • C.I. N° 56298									
		8	7-8	5	200	5	1,5	5	5
<b>NOVA YELLOW ST H4G</b> C.I. Pigment Yellow 151 • C.I. N° 13980									
		8	8	5	160	5	1,6	5	5
<b>NOVA YELLOW ST H3G</b> C.I. Pigment Yellow 154 • C.I. N° 11781									

The technical data above stated are presented in good faith and to the best of our knowledge. They should serve only as approximate guidance and therefore customers are kindly advised to test and ascertain the performance of our products in the operating conditions existing at their end, to satisfy themselves about their suitability in a given industrial application.















**NOVACHEM**

## ORGANIC PIGMENTS

FOR PAINT AND COATINGS, PLASTIC MATERIALS,  
LEATHER AND OTHER SPECIAL APPLICATIONS



NOVA

FULL SHADE	TINT SHADE	LIGH FASTNESS		WEATHER FASTNESS	CHEMICAL FASTNESS				
		FULL SHADE	1/25 ST SHADE		FULL SHADE	HEAT C°	OVER SPRAY	DENSITY g/cm <sup>3</sup>	HCL 2,5%
		7-8	7	4-5	180	5	1,4	5	5
<b>NOVA YELLOW ST 4G</b> C.I. Pigment Yellow 155 • C.I. N° 200310									
		7-8	7	4-5	180	5	1,5	5	5
<b>NOVA YELLOW 5 GDB</b> C.I. Pigment Yellow 155 • C.I. N° 200310									
		8	7-8	5	160	4-5	1,4	5	5
<b>NOVA YELLOW ST H6G</b> C.I. Pigment Yellow 175 • C.I. N° 11784									
		7-8	7-8	5	200	5	5,6	4-5	4-5
<b>NOVA YELLOW OXIDE BV</b> C.I. Pigment Yellow 184 • C.I. N° 771740									
		7-8	7-8	4-5	200	5	6,1	4-5	4-5
<b>NOVA YELLOW OXIDE BV-R</b> C.I. Pigment Yellow 184 • C.I. N° 771740									
		6	5	4-5	180	5	1,5	5	3
<b>NOVA YELLOW ST 55 D</b> C.I. Pigment Yellow 185 • C.I. N° 56290									
		7-8	7-8	4-5	200	5	1,4	5	5
<b>NOVA YELLOW F2G</b> C.I. Pigment Yellow 194 • C.I. N° 11785									















The technical data above stated are presented in good faith and to the best of our knowledge. They should serve only as approximate guidance and therefore customers are kindly advised to test and ascertain the performance of our products in the operating conditions existing at their end, to satisfy themselves about their suitability in a given industrial application.

## ORGANIC PIGMENTS

FOR PAINT AND COATINGS, PLASTIC MATERIALS,  
LEATHER AND OTHER SPECIAL APPLICATIONS



NOVA

FULL SHADE	TINT SHADE	LIGHT FASTNESS		WEATHER FASTNESS FULL SHADE	CHEMICAL FASTNESS					
		FULL SHADE	1/25 ST SHADE		HEAT C°	OVER SPRAY	DENSITY g/cm <sup>3</sup>	HCL 2,5%	NaOH 2,5%	
		6-7	6	3-4	200	4	1,4	5	5	
<b>NOVA ORANGE RL 70</b> C.I. Pigment Orange 34 • C.I. N° 21115										
		6	5	3	200	4	1,4	5	5	
<b>NOVA ORANGE RL</b> C.I. Pigment Orange 34 • C.I. N° 21115										
		8	7-8	5	160	5	1,6	5	5	
<b>NOVA ORANGE HL 70</b> C.I. Pigment Orange 36 • C.I. N° 11780										
		8	7	4-5	160	5	1,6	5	5	
<b>NOVA ORANGE HL</b> C.I. Pigment Orange 36 • C.I. N° 11780										
		6-7	7-8	4	200	5	1,9	5	5	
<b>NOVA ORANGE GR</b> C.I. Pigment Orange 43 • C.I. N° 71105										
		8	7-8	4	250	5	1,6	5	5	
<b>NOVA ORANGE GS</b> C.I. Pigment Orange 64 • C.I. N° 12760										
		8	8	5	200	5	1,3	5	5	
<b>NOVA FAST ORANGE RA</b> C.I. Pigment Orange 73 • C.I. N° 561170										

The technical data above stated are presented in good faith and to the best of our knowledge. They should serve only as approximate guidance and therefore customers are kindly advised to test and ascertain the performance of our products in the operating conditions existing at their end, to satisfy themselves about their suitability in a given industrial application.















**NOVACHEM**

## ORGANIC PIGMENTS

FOR PAINT AND COATINGS, PLASTIC MATERIALS,  
LEATHER AND OTHER SPECIAL APPLICATIONS



NOVA

FULL SHADE	TINT SHADE	LIGH FASTNESS		WEATHER FASTNESS FULL SHADE	CHEMICAL FASTNESS				
		FULL SHADE	1/25 ST SHADE		HEAT C°	OVER SPRAY	DENSITY g/cm <sup>3</sup>	HCL 2,5%	NaOH 2,5%
		7-8	7	4-5	200	4	1,6	4-5	2
<b>NOVA RED 2 BH</b> C.I. Pigment Red 48:4 • C.I. N° 15865:4									
		7-8	6	4	150	4	1,5	4	2
<b>NOVA RED BH</b> C.I. Pigment Red 52:2 • C.I. N° 15860:2									
		7-8	6	4-5	150	2	1,5	5	4
<b>NOVA RED ST 211</b> C.I. Pigment Red 112 • C.I. N° 12370									
		7-8	6-7	4-5	180	2	1,5	5	4
<b>NOVA RED ST 211-70</b> C.I. Pigment Red 112 • C.I. N° 12370									
		7-8	7-8	4	200	5	1,5	5	5
<b>NOVA RED ST 600</b> C.I. Pigment Red 122 • C.I. N° 73915									
		7-8	7-8	4	200	5	1,5	5	5
<b>NOVA RED ST 600-02</b> C.I. Pigment Red 122 • C.I. N° 73915									
		6-7	5-6	4	200	4	1,5	5	5
<b>NOVA FAST RED 3163</b> C.I. Pigment Red 123 • C.I. N° 71145									

The technical data above stated are presented in good faith and to the best of our knowledge. They should serve only as approximate guidance and therefore customers are kindly advised to test and ascertain the performance of our products in the operating conditions existing at their end, to satisfy themselves about their suitability in a given industrial application.















**NOVACHEM**

## ORGANIC PIGMENTS

FOR PAINT AND COATINGS, PLASTIC MATERIALS,  
LEATHER AND OTHER SPECIAL APPLICATIONS



NOVA

FULL SHADE	TINT SHADE	LIGH FASTNESS		WEATHER FASTNESS	CHEMICAL FASTNESS					
		FULL SHADE	1/25 ST SHADE		FULL SHADE	HEAT C°	OVER SPRAY	DENSITY g/cm <sup>3</sup>	HCL 2,5%	NaOH 2,5%
		8	7-8	5	200	5	1,5	5	5	
<b>NOVA RED BR</b> C.I. Pigment Red 144 • C.I. N° 20735										
		5-6	4-5	2-3	180	4	1,4	5	5	
<b>NOVA RED FBB</b> C.I. Pigment Red 146 • C.I. N° 12485										
		8	7	3	240	5	1,4	5	5	
<b>NOVA FAST RED 1963 FB</b> C.I. Pigment Red 149 • C.I. N° 71137										
		7-8	7	5	280	5	1,5	5	5	
<b>NOVA SCARLET RN</b> C.I. Pigment Red 166 • C.I. N° 20730										
		8	7-8	5	180	5	2,0	5	5	
<b>NOVA SCARLET ST-GO</b> C.I. Pigment Red 168 • C.I. N° 59300										
		6-7	4-5	3	160	5	1,4	5	5	
<b>NOVA RED 1462</b> C.I. Pigment Red 170 • C.I. N° 12475										
		7	5	3-4	160	5	1,4	5	5	
<b>NOVA RED FRK3</b> C.I. Pigment Red 170 • C.I. N° 12475										















The technical data above stated are presented in good faith and to the best of our knowledge. They should serve only as approximate guidance and therefore customers are kindly advised to test and ascertain the performance of our products in the operating conditions existing at their end, to satisfy themselves about their suitability in a given industrial application.

**NOVACHEM**

**ORGANIC PIGMENTS**  
FOR PAINT AND COATINGS, PLASTIC MATERIALS,  
LEATHER AND OTHER SPECIAL APPLICATIONS



NOVA

FULL SHADE	TINT SHADE	LIGH FASTNESS		WEATHER FASTNESS FULL SHADE	CHEMICAL FASTNESS					
		FULL SHADE	1/25 ST SHADE		HEAT C°	OVER SPRAY	DENSITY g/cm <sup>3</sup>	HCL 2,5%	NaOH 2,5%	
		7	5-6	4-5	160	5	1,4	5	5	
<b>NOVA RED FRK2</b> C.I. Pigment Red 170 • C.I. N° 12475										
		7	6	4-5	200	4-5	1,6	5	5	
<b>NOVA RED HF 3C</b> C.I. Pigment Red 176 • C.I. N° 12515										
		8	6-7	4-5	200	5	1,5	5	5	
<b>NOVA RED A3B</b> C.I. Pigment Red 177 • C.I. N° 65300										
		7-8	7	4-5	200	5	1,5	5	5	
<b>NOVA FAST RED 1931</b> C.I. Pigment Red 179 • C.I. N° 71130										
		7-8	7	5	200	5	1,5	5	5	
<b>NOVA FAST RED 2010</b> C.I. Pigment Red 179 • C.I. N° 71130										
		5	4-5	3	180	5	1,4	5	5	
<b>NOVA RUBINE ST-F6B</b> C.I. Pigment Red 184 • C.I. N° 12487										
		7	6	4	180	5	1,45	5	5	
<b>NOVA RED HF 4C</b> C.I. Pigment Red 185 • C.I. N° 12516										















The technical data above stated are presented in good faith and to the best of our knowledge. They should serve only as approximate guidance and therefore customers are kindly advised to test and ascertain the performance of our products in the operating conditions existing at their end, to satisfy themselves about their suitability in a given industrial application.

## ORGANIC PIGMENTS

FOR PAINT AND COATINGS, PLASTIC MATERIALS,  
LEATHER AND OTHER SPECIAL APPLICATIONS



NOVA

FULL SHADE	TINT SHADE	LIGH FASTNESS		WEATHER FASTNESS FULL SHADE	CHEMICAL FASTNESS				
		FULL SHADE	1/25 ST SHADE		HEAT C°	OVER SPRAY	DENSITY g/cm <sup>3</sup>	HCL 2,5%	NaOH 2,5%
		7	6	4	200	5	1,44	5	5
<b>NOVA RED HF 3S</b> C.I. Pigment Red 188 • C.I. N° 12467									
		7	6	4-5	200	4	1,44	5	5
<b>NOVA RED HF 3S-70</b> C.I. Pigment Red 188 • C.I. N° 12467									
		6	6	4	200	5	1,4	5	5
<b>NOVA FAST RED HF 2B</b> C.I. Pigment Red 208 • C.I. N° 12514									
		8	6-7	4	200	5	1,5	5	5
<b>NOVA RED BRN</b> C.I. Pigment Red 214 • C.I. N° 200660									
		7-8	7	4	200	5	1,5	5	5
<b>NOVA SCARLET RF</b> C.I. Pigment Red 242 • C.I. N° 20067									
		8	8	4-5	200	5	1,6	5	5
<b>NOVA RED DPP 03</b> C.I. Pigment Red 254 • C.I. N° 56110									
		7-8	7-8	3	200	5	1,6	5	5
<b>NOVA RED VIOLET E5B</b> C.I. Pigment Violet 19 • C.I. N° 73900									

The technical data above stated are presented in good faith and to the best of our knowledge. They should serve only as approximate guidance and therefore customers are kindly advised to test and ascertain the performance of our products in the operating conditions existing at their end, to satisfy themselves about their suitability in a given industrial application.

**NOVACHEM**

















## ORGANIC PIGMENTS

FOR PAINT AND COATINGS, PLASTIC MATERIALS,  
LEATHER AND OTHER SPECIAL APPLICATIONS



NOVA

FULL SHADE	TINT SHADE	LIGTH FASTNESS		WEATHER FASTNESS FULL SHADE	CHEMICAL FASTNESS				
		FULL SHADE	1/25 ST SHADE		HEAT C°	OVER SPRAY	DENSITY g/cm <sup>3</sup>	HCL 2,5%	NaOH 2,5%
		8	7-8	3-4	200	5	1,5	5	5
<b>NOVA VIOLET ST 4921 VG</b> C.I. Pigment Violet 19 • C.I. N° 73900									
		7-8	7	4-5	200	5	1,5	5	5
<b>NOVA VIOLET RL/P</b> C.I. Pigment Violet 23 • C.I. N° 51319									
		7-8	7	4-5	220	5	1,5	5	5
<b>NOVA VIOLET RB</b> C.I. Pigment Violet 23 • C.I. N° 51319									
		6	4	2-3	200	5	1,39	5	5
<b>NOVA RED VIOLET HF3R</b> C.I. Pigment Violet 32 • C.I. N° 12517									
		7-8	7-8	5	200	5	1,7	5	5
<b>NOVA BLUE ST 151-WMP</b> C.I. Pigment Blue 15:1 • C.I. N° 74160									
		7-8	7-8	5	200	5	1,7	5	5
<b>NOVA BLUE ST 151</b> C.I. Pigment Blue 15:1 • C.I. N° 74160									
		7-8	7-8	5	200	5	1,6	5	5
<b>NOVA BLUE ST 152</b> C.I. Pigment Blue 15:2 • C.I. N° 74160									















The technical data above stated are presented in good faith and to the best of our knowledge. They should serve only as approximate guidance and therefore customers are kindly advised to test and ascertain the performance of our products in the operating conditions existing at their end, to satisfy themselves about their suitability in a given industrial application.

## ORGANIC PIGMENTS

FOR PAINT AND COATINGS, PLASTIC MATERIALS,  
LEATHER AND OTHER SPECIAL APPLICATIONS



NOVA

FULL SHADE	TINT SHADE	LIGH FASTNESS		WEATHER FASTNESS FULL SHADE	CHEMICAL FASTNESS				
		FULL SHADE	1/25 ST SHADE		HEAT C°	OVER SPRAY	DENSITY g/cm <sup>3</sup>	HCL 2,5%	NaOH 2,5%
		7-8	7-8	5	200	5	1,6	5	5
<b>NOVA BLUE ST 153 UV</b> C.I. Pigment Blue 15:3 • C.I. N° 74160									
		7-8	7-8	5	200	5	1,6	5	5
<b>NOVA BLUE ST 154</b> C.I. Pigment Blue 15:4 • C.I. N° 74160									
		8	8	5	200	5	1,48	5	5
<b>NOVA BLUE A3R</b> C.I. Pigment Blue 60 • C.I. N° 69800									
		8	8	5	200	5	1,5	5	5
<b>NOVA BROWN HFR 01</b> C.I. Pigment Brown 25 • C.I. N° 12510									
		8	8	5	200	5	2,1	5	5
<b>NOVA GREEN GS3</b> C.I. Pigment Green 7 • C.I. N° 74260									
		8	8	5	200	5	2,8	5	5
<b>NOVA GREEN 8G</b> C.I. Pigment Green 36 • C.I. N° 74265									
		8	6	4	200	3-4	1,5	5	5
<b>NOVA FAST BLACK 3194</b> C.I. Pigment Black 32 • C.I. N° 71133									

The technical data above stated are presented in good faith and to the best of our knowledge. They should serve only as approximate guidance and therefore customers are kindly advised to test and ascertain the performance of our products in the operating conditions existing at their end, to satisfy themselves about their suitability in a given industrial application.

**NOVACHEM**